

CLASSIFICATION REPORT OF FIRE RESISTANCE

IN ACCORDANCE WITH ÖNORM EN 13501-2:2016

24.08.2021
POS/FÜI

Customer: Stora Enso Wood Products GmbH
Brand 44
AT-3531 Brand

Prepared by: Holzforschung Austria
Franz Grill-Straße 7
AT-1030 Wien

Subject: Load-bearing wall components of cross laminated timber
„Stora Enso CLT 100 mm“ planked and unplanked
Fire resistance REI 90/REI 120

Nr. of classification report: 2603/2020/02 – BH

Number of edition : 02

Date of edition: 24.08.2021

Pages: 6

Enclosures: ---
:

1. Introduction

This classification report on fire resistance defines the classification of load-bearing wall components of cross laminated timber "Stora Enso CLT 100 mm" planked and unplanked, in compliance with the process according to the standard ÖNORM EN 13501-2:2016.

2. Details on the classified product

2.1. General

The load-bearing wall components of cross laminated timber "Stora Enso CLT 100 mm" planked and unplanked belong to the product type of load-bearing, insulating solid timber constructions.

2.2. Description

Table 1: components to be classified

planking mm room side	installation level/ dry lining	cross laminated timber dimensions (layers) mm
≥ 12,5 GKF*)	---	CLT 100 C3s 100 mm (3s - 30 40 30) according ETA-14/0349 AbZ: Z-9.1-559
≥ 12,5 GKF*)	40 mm mineralwool**	CLT 100 C3s 100 mm (3s – 30 40 30) according ETA-14/0349 AbZ: Z-9.1-559

*) according to ÖNORM B 3410; DIN 18180; type DF according to ÖNORM EN 520; density ≥ 800 kg/m³ or gypsum fibre board according to ÖNORM EN 15283-2; density ≥ 1000 kg/m³

**) mineralwool according ÖNORM EN 13162; density ≥ 11 kg/m³

3. Test reports/reports on the extended area of application and test result for verification of the classification

3.1. Description of the underlying tested components

Table 2: tested cross laminated timber components

short name	planking mm exposed side to fire	cross laminated timber dimensions mm (layers)	planking mm non exposed side to fire
---	12,5 GKF*)	CLT 100 (30 40 30)	---
MW 3.1	40 MW**) 12,5 GKF*)	CLT 97 (35 27 35)	---

*) according to ÖNORM B 3410; DIN 18180; type DF according to ÖNORM EN 520; density ≥ 800 kg/m³

**) MW - mineralwool according ÖNORM EN 13162; density ≥ 11 kg/m³

3.2. Test reports

Table 3: underlying test reports

test laboratory	name of the costumer	test report n°	standard and issue date	type of product/ test specimen
MA 39 ¹⁾	Stora Enso Wood Products OY 00160 Helsinki	MA 39 – 21-04436	ÖNORM EN 1365-1: 2013-07 ÖNORM EN 1363-1: 2020-04	test report on the fire resistance of a load- bearing wall of cross laminated timber „CLT 3s with GK- planking“ (tested on 17.03.2021)
MA 39 ¹⁾	Holzfor- schung Austria	MA 39 – VFA 2010-1377.04	ÖNORM EN 1365-1: 2000-04 ÖNORM EN 1363-1: 2000-01	test report on the fire resistance of a load- bearing wall of cross laminated timber „Stora Enso CLT 3s“ planked with one layer GKF board and an insulated installa- tion area with glas- wool

1) MA 39 – Magistrat der Stadt Wien, Magistratsabteilung 39, Prüf-, Überwachungs- und Zertifizierungsstelle der Stadt Wien

The test reports listed under point 3.2. according to ÖNORM EN 1365-1 and 1363-1 were partly carried out according to older standards (see table 3).

The current standards, ÖNORM EN 1365-1: 2013 and ÖNORM EN 1363-1:2020, essentially contain changes in terminology, new definitions and concretisations compared to the older versions.

According to information from the testing body, these changes have no effect on the results in the test reports listed and can therefore still be used for the classification of fire resistance.

3.3. Results

Table 4: results

testing process: ÖNORM EN 1365-1: 2013-07 ÖNORM EN 1363-1: 2020-04	parameters	results
test report n° MA 39 – 21-04436	<i>load applied</i>	150 kN total load
	<i>supporting structure</i>	50 kN/m
	<i>load-bearing capacity</i>	92 min
	<i>integrity</i>	92 min
	<i>thermal insulation</i>	92 min
testing process: ÖNORM EN 1365-1: 2000-04 ÖNORM EN 1363-1: 2000-01	parameters	results
test report n° MA 39 – VFA 2010-1377.04	load applied	105 kN total load
	supporting structure	35 kN/m
	load-bearing capacity	122 min
	integrity	122 min

4. Classification and area of application

4.1. Classification reference

This classification was carried out in compliance with ÖNORM EN 13501-2:2016-11, clause 7.3.2..

4.2. Classification

The load-bearing walls of cross laminated timber are classified according to the following combinations of performance parameters and classes.

Wall height ≤ 3 m

fire resistance of the constructions listed in 2.2. fire exposed side	test report n°	R	E	I	applied load E_{d,fi} kN/m
CLT 100 C3s (3s - 30 40 30) 12,5 GKF*)	MA 39 – 21-04436	90	90	90	50
CLT 100 C3s (3s - 30 40 30) 40 MW**) 12,5 GKF*)	MA 39 – VFA 2010-1377.04	120	120	120	35

*) according to ÖNORM B 3410; DIN 18180; type DF according to ÖNORM EN 520; density ≥ 800 kg/m³ or gypsum fibre board according to ÖNORM EN 15283-2; density ≥ 1000 kg/m³

***) MW according ÖNORM EN 13162; density ≥ 11 kg/m³

4.3. Area of application

This classification is valid for the following practical applications:

The classification result may be transferred directly to similar cross laminated timber walls in which one or several of the following changes are made and in which the design continues to meet the requirements of the relevant design standard with regard to stiffness and strength:

- Reducing the height of the wall
- Increasing the width of the wall
- Increasing the structure's thickness
- Increasing the thickness of the corresponding materials
- Reducing the length of boards or panels but not the thickness
- Reducing the load applied
- Installation of additional non-flammable materials in the construction

5. Limitations

5.1. General

If one of the fundamental test and evaluation criteria changes or the customer makes prohibited technical changes to the product, this classification report shall cease to be valid.

5.2. Warning notice

This classification document does not constitute a type approval or certification of the product.

HOLZFORSCHUNG AUSTRIA


DI Sylvia Polleres

Authorised signatory and technical consultant

DI Simon Winter

This report was approved electronically in accordance with an internal HFA process by the designated authorized signatory, traceable and documented.

Accreditation is given for the following procedures.
 It is not allowed to use included accreditation marks for own purposes.

accreditation mark	type of accreditation	process
	inspection	<ul style="list-style-type: none"> • ÖNORM EN 13501-2

Publication in excerpts is only permitted with the written approval of Holzforschung Austria.
 In case of dispute the original German version prevails. This translation is for information purposes only.